



BODY SPRAY FILL

Technical Data Sheet No 825

VOC compliant with the regulations

It is compatible with all type of paints and primers

It can be combined with 1K and 2K topcoats as well as metallic effect paints. 1K primers, 2K acrylic and epoxy primers, 1K and 2K clear coats

Contains universal thinner and propellant gas

General Technical Description

2-3 passes

Dust free 10-12 mins at 18-23 °C

Surface

On old, sanded paint work

Metal or wooden surfaces

OEM surfaces

Clean and sanded steel panels

HB Body Polyester Filler

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

Product Application: »» For 1K top coats and primers as well as metallic effect paints you need to fill 100 ml. For 2K primers, top coats and clear coats you need to fill 80 ml and 20 ml BODY CONVERTER. For high viscous 2K primers and top coats you need to fill 70 ml and 20 ml BODY CONVERTER and 10 ml BODY ACRYLIC THINNER NORMAL.



Shake well before using



2-3 coats approximately 20-30 microns.



Dust free 10min at 23 °C



Full hardness within 24 hours.

Flash Point:
-97°C

Specific Gravity:
0.80 g/cm³

Solid Content (No thinner):
- Weight

VOC (2004/42/EC)
This is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 365g/L.
2004/42/IIIB(e)(840)365

Theoretical Coverage:
-

Cleaning of equipment:
-

Remarks:

- Always try to use the product in accordance with the specifications provided.
- It can be used by countries that do not adopt the VOC legislation as well.
- Shake thoroughly before use.
- Shake for 2-3min after agitator ball has started to rattle.
- After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.
- Optimum operating temperature range 10-25°C

Shelf life:

- Up to 36 months unused spray.
- +5 to +25 °C

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 3 / 2015, September 2015